

# VICTREX ST™ POLYMER 45GL30

## General Information

### Product Description

High performance thermoplastic material, 30% glass fibre reinforced PolyEtherKetoneEtherKetoneKetone (PEKEKK), semi crystalline, granules for injection moulding, standard flow, colour natural/beige.

Applications for higher strength and stiffness at elevated temperatures. Low coefficient of thermal expansion. Chemically resistant to aggressive environments.

## Material Properties

Physical	Nominal Value	Unit	Test Method
Density (Crystalline)	1.53	g/cm <sup>3</sup>	ISO 1183
Spiral Flow			Internal Method
-- 1	10.0	cm	
-- 2	44.0	cm	
Molding Shrinkage <sup>3</sup>			ISO 294-4
Across Flow	0.90	%	
Flow	0.30	%	
Water Absorption - Saturation (100°C)	0.60	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	12000	MPa	ISO 527-1
Tensile Stress			ISO 527-2
Break, 23°C	195	MPa	
Break, 125°C	130	MPa	
Break, 175°C	80.0	MPa	
Break, 275°C	50.0	MPa	
Tensile Strain (Break, 23°C)	2.8	%	ISO 527-2
Flexural Modulus (23°C)	11000	MPa	ISO 178
Flexural Stress			ISO 178
23°C	280	MPa	
125°C	180	MPa	
175°C	120	MPa	
275°C	70.0	MPa	
Compressive Stress			ISO 604
23°C	290	MPa	
120°C	190	MPa	
200°C	75.0	MPa	
250°C	50.0	MPa	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.0	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	70.0	kJ/m <sup>2</sup>	ISO 179/1U
Notched Izod Impact Strength (23°C)	11.0	kJ/m <sup>2</sup>	ISO 180/A
Unnotched Izod Impact Strength (23°C)	60.0	kJ/m <sup>2</sup>	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/Af
1.8 MPa, Unannealed	380	°C	

# VICTREX ST™ POLYMER 45GL30

<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Glass Transition Temperature			ISO 11357-2
Onset	162	°C	
Midpoint	169	°C	
Melting Temperature	387	°C	ISO 11357-3
CLTE - Flow			ISO 11359-2
< 162°C	21	ppm/K	
> 162°C	23	ppm/K	
CLTE - Average			ISO 11359-2
< 162°C	40	ppm/K	
> 162°C	100	ppm/K	
Thermal Conductivity			ISO 22007-4
23°C <sup>4</sup>	0.30	W/m/K	
23°C <sup>5</sup>	0.35	W/m/K	
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Volume Resistivity (23°C)	1.0E+16	ohms-cm	IEC 60093
Dielectric Strength (2.00 mm)	22.0	kV/mm	IEC 60243-1
Dielectric Constant (23°C, 1 kHz)	3.30		IEC 60250
Dissipation Factor (23°C, 1 MHz)	4.0E-3		IEC 60250
Comparative Tracking Index	150	V	IEC 60112
<b>Fill Analysis</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Melt Viscosity (420°C)	600	Pa·s	ISO 11443

## Typical Processing Information

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature	150 to 180	°C
Drying Time	3.0 to 6.0	hr
Hopper Temperature	< 100	°C
Rear Temperature	385	°C
Middle Temperature	395 to 400	°C
Front Temperature	405	°C
Nozzle Temperature	410	°C
Mould Temperature	200 to 220	°C

### Injection Notes

Runner: Die / nozzle >3mm, manifold >3.5mm

Gate: >2mm or 0.5 x part thickness

Important notes:

1) Processing conditions quoted in our datasheets are typical of those used in our processing laboratories

- Data for mould shrinkage should be used for material comparison. Actual mould shrinkage values are highly dependent on part geometry, mould configuration, and processing conditions.
- Mould shrinkage differs for along flow and across flow directions. "Along flow" direction is taken as the direction the molten material is travelling when it exits the gate and enters the mould.
- Mould shrinkage is expressed as a percent change in dimension of a specimen in relation to mould dimensions.

2) Data are generated in accordance with prevailing national, international and internal standards, and should be used for material comparison. Actual property values are highly dependent on part geometry, mould configuration and processing conditions. Properties may also differ for along flow and across flow directions.

Detailed data available on our website [www.victrex.com](http://www.victrex.com) or upon request.

# VICTREX ST™ POLYMER 45GL30

## Notes

<sup>1</sup> Mould Temperature: 210°C, Melt Temperature: 410°C, 1.00 mm

---

<sup>2</sup> Mould Temperature: 210°C, Melt Temperature: 410°C, 3.00 mm

---

<sup>3</sup> 410°C nozzle, 210°C tool

---

<sup>4</sup> Average

---

<sup>5</sup> Along flow

---

**Revision Date: December 2023**

This information is provided "as is". It is not intended to amount to advice. Use of the product is at the customer's/user's risk. It is the customer's/user's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy and safety for each end-use product, device or other application and compliance with applicable laws, regulations and standards. Mention of a product is no guarantee of availability. Victrex reserves the right to modify products, data sheets, specifications and packaging. **Victrex makes no warranties, express or implied (including, without limitation, any warranty of fitness for a particular purpose or of intellectual property non-infringement) and will not be liable for any loss or damage of any nature (however arising) in connection with customer's/user's use or reliance on this information, except for any liability which cannot be excluded or limited by law.** This document may be modified or retracted at any time without notice to the customer/user.

Victrex Manufacturing Limited (or another member of the Victrex group) is the owner or the licensee of all intellectual property rights in and to this document including the following trademarks, VICTREX, INVIBIO, JUVORA, APTIV, 450G, PEEK-OPTIMA, SHAPING FUTURE PERFORMANCE, LMPAEK, TRIANGLE (Device). All rights are protected by intellectual property rights including copyright under relevant national and international intellectual property laws and treaties. All rights reserved. Copyright © Victrex Manufacturing Limited 2023.